

RMV® Compound, Multi-Plied Monofilament Carcass

Outstanding achievement in non-stick performance

- Goodyear's RMV compound is FDA and USDA compliant and offers:
 - superior resistance to animal fats, vegetable and mineral oils
 - high resin content offers state-of-the-art Melt-Weld fabrications
- Quadgrip cover profile:
 - good release characteristics when conveying sticky pastries and dough
 - improved grip for incline service
- Multi-Plied Monofilament carcass with HPC[™] technology:
 - excellent transverse rigidity
 - superior tracking in both directions
 - resistance to edge wicking and curling
 - flexibility over small pulleys
 - Thermo-Flo™ splicing capabilities

Description	Plies	Working Tension		Approx. OAG		Weight		COF	Pulley Dia.		Temp.	
		PIW*	KN/m	in.	mm	Lbs./Sq.ft.	Kg/Sq.m	(approx.)	ln.	mm	°F°	С
RMV 100RM QLw	2	100	18	0.095	2.4	0.55	2.7	0.18	2.0	51	20-180	-7-82

^{*}Elongation less than 2% at specified PIW

Description	Splicing Methods	Recommended Fasteners**			
2000	opnomy memoria	Clipper	Alligator	Staple	
RMV 100RM QLw	Finger-over-finger, Finger, Bias Stepped, Skived Bias, Mechanical Fasteners	36SP or UCM36SP	1	62	

^{**} Fastener manufacturer should be consulted to review specific belt and application information