

MEDIA	H	N	U/HF UFR	PV	NC	O	OC	PFX	HFR	FEP	TFE
Sevin (insecticides in water)	G	G	G	-	-	-	-	G	G	-	G
Silicone Greases	G	G	G	G	G	-	-	G	G	-	G
Silicone Oils	G	G	G	G	G	-	-	G	G	-	G
Skydrol 500 & 7000	L	G	P	P	G	P	P	P	L	G	G
Soap Solutions	G	G	G	G	G	G	G	G	G	G	G
Soda Water	G	G	G	G	G	3	3	G	G	-	G
Sodium Borate	G	G	G	G	G	G	G	G	G	G	G
Sodium Carbonate	3	3	3	3	3	3	3	3	3	3	3
Sodium Chloride Solutions	G	G	G	G	3	G	-	G	G	G	G
Sodium Hydroxide, 50%	L	P	P	L	P	L	L	P	L	G	G
Sodium Hypochlorite	L	P	P	L	-	3	3	P	L	G	G
Steam	P	P	P	P	P	P	P	P	P	G	G
Stoddard Solvent	P	G	P	L	G	P	P	P	P	G	G
Straight Synthetic Oils (phosphate esters)	L	G	P	P	G	-	-	P	L	-	G
Sulfur	G	G	G	G	-	L	G	G	G	G	G
Sulfur Dioxide	P	L	L	L	-	P	-	L	P	G	G
Sulfur Hexafluoride Gas (4) (5)	G	G	G	G	-	G	-	G	G	-	G
Sulphuric Acid	P	P	P	3	P	P	P	P	P	-	G
Toluene	L	G	L	P	G	P	P	P	L	G	G
Toloul	L	G	L	P	G	P	P	P	L	-	G
Transmission Fluid	G	G	G	P	G	-	-	G	G	-	G
Trichloroethylene	P	L	P	L	G	P	P	P	P	G	G
Trisodium Phosphate Solutions	L	G	P	G	G	G	G	P	L	G	G
Turpentine	G	G	L	L	G	P	P	P	G	G	G
Ucon (hydraulic fluid-water glycol base)	G	G	L	G	G	-	-	L	G	-	G
Varnish	G	G	G	P	G	G	L	G	G	-	G
Vinegar (6)	L	G	L	G	G	G	G	L	L	G	G
Water (to 135°F) (6)	G	G	G	G	G	G	G	L	G	G	G
Water (above 135°F) (6)	P	G	P	L	-	P	P	P	P	L	G
Water Glycols (to 135°F)	L	G	L	G	G	L	L	L	G	-	G
Water Glycols (above 135°F)	P	G	P	L	-	P	P	P	P	-	G
Water in oil Emulsions (to 135°F)	G	G	L	G	G	-	-	L	G	-	G
Water in oil Emulsions (above 135°F)	P	G	P	L	-	-	-	P	P	-	G
Whiskey, Wines (6)	G	G	L	G	G	G	G	G	G	G	G
Wood Oils	G	G	L	G	G	-	-	G	G	-	G
Xylene	L	G	P	P	G	P	P	P	L	G	G
Zinc Chloride	G	G	G	G	P	G	G	G	G	G	G

Footnotes for Fluid Compatibility Guides: (1) The Fluid Compatibility Guides are simplified rating tabulations based on immersion tests at 75°F. Higher temperatures tend to reduce ratings. Since final selection depends on pressure, fluid and ambient temperature and other factors not known to Parker Hannifin Co., no performance guarantee is expressed or implied. Ratings do not imply compliance with specialized codes such as FDA, NSF, AGA or UL and do not cover possible fluid discoloration, taste or odor effects. For conveying foodstuffs use FDA sanctioned materials, and for potable water use NSF listed materials. For chemicals not listed, or for advice on particular applications, please consult Product Engineering, Parflex Div., Ravenna, Ohio. (2) Hose applications for these fluids must take into account legal and insurance regulations. This does not imply AGA or UL compliance. (3) Satisfactory at some concentrations and temperatures, unsatisfactory in others. (4) For high pressure gases, the cover should be pinpricked and the pressure must not be released quickly. Chain or restrain the hose to prevent personal injury in the event of damage or failure. (5) Chemical compatibility does not imply low permeation rates. Consult the Parker factory for a recommendation for your specific requirement. (6) Does not imply NSF or FDA compliance. (7) Chemical compatibility does not imply acceptability for use in airless paint spray applications. These applications require a special conductive hose. (8) Teflon is chemically compatible with Anhydrous Ammonia. However, extreme caution must be used in dealing with Anhydrous Ammonia since it can cause severe injuries such as blindness and/or chemical burns.

Hydraulic & Pneumatic Hose & Fit.

PTFE Hose & Fittings

Thermoplastic Tubing

Coiled Air Hose, Fittings & Accessories

Truck (Fleet) Products

Tooling & Equipment

Hose Accessories

Technical & Design Information

Approvals & Guides

anumeric Index